

Iten Industries

Radiolucent X-Ray Panel Performance Values

<u>Properties</u>	<u>Test Condition</u>	<u>ASTM</u>	<u>Values</u>
Thickness			.125 inches
Tensile Strength:	Lengthwise	D638	22,900 psi
	Crosswise		15,200 psi
Flexural Strength:	Condition A Lengthwise	D790	32,900 psi
	Condition A Crosswise		25,600 psi
	D48/50 Lengthwise		24,800 psi
	D48/50 Crosswise		18,800 psi
Compressive Strength:	Lengthwise	D695	19,400 psi
	Crosswise		17,200 psi
Izod Impact (notched):	Condition A Lengthwise	D256	0.64 ft.lb./in.
	Condition A Crosswise		0.51 ft.lb./in.
	D48/50 Lengthwise		0.93 ft.lb./in.
	D48/50 Crosswise	D256	0.89 ft.lb./in.
	E48/50 Lengthwise		0.67 ft.lb./in.
	E48/50 Crosswise		0.50 ft.lb./in.
Water Absorption		D570	1.96% of weight
Specific Gravity		D792	1.42
U.L. Subject 94		UL94	94HB
Dielectric Strength		D149	314+ Vpm
Dielectric Breakdown:	Condition A	D149	65.0 kV
	D48/50		4.5 kV
Arc Resistance:	Condition A	D495	49 seconds
	D48/50		12.1 seconds
Permittivity, 1MHz:	Condition A	D150	4.88
	D24/23		5.80
Dissipation Factor, 1MHz:	Condition A	D150	0.0426
	D24/23		0.0627
Permittivity, 1KHz:	Condition A	D150	5.99
	D24/23		9.20
Dissipation Factor, 1KHz:	Condition A	D150	0.0993
	D24/23		0.3119

Standard Sheet sizes are 36" x 48", 48" x 48", 48" x 72", & 48" x 96"

Ashtabula, Ohio 44004 440-997-6134 Fax 440-992-3614
and
Addison, Illinois 60101 630-543-2880 Fax 630-543-1463

All values are average test results from typical production material. No warranty is implied or guaranteed and testing is recommended for each application.

www.itenindustries.com

Imageneering with Plastics

November 23, 2000