

Iten Industries

Resiten® 112 Performance Values

<u>Properties</u>	<u>Test Condition</u>	<u>ASTM</u>	<u>Values</u>
Thickness			.125 inches
Tensile Strength:	Lengthwise	D638	23,900 psi
	Crosswise		16,100 psi
Flexural Strength:	Condition A Lengthwise	D790	29,300 psi
	Condition A Crosswise		23,800 psi
	D48/50 Lengthwise		26,600 psi
	D48/50 Crosswise		21,600 psi
Compressive Strength:	Lengthwise	D695	20,000 psi
	Crosswise		17,500 psi
Izod Impact (notched):	Condition A Lengthwise	D256	0.55 ft.lb./in.
	Condition A Crosswise		0.46 ft.lb./in.
	D48/50 Lengthwise		0.68 ft.lb./in.
	D48/50 Crosswise	D256	0.59 ft.lb./in.
	E48/50 Lengthwise		0.53 ft.lb./in.
	E48/50 Crosswise		0.46 ft.lb./in.
Water Absorption		D570	1.28% of weight
Specific Gravity		D792	1.40
U.L. Subject 94		UL94	94HB
Dielectric Strength		D149	365 Vpm
Dielectric Breakdown:	Condition A	D149	79.1 kV
	D48/50		6.5 kV
Arc Resistance:	Condition A	D495	31 seconds
	D48/50		20 seconds
Comparative Track Index (CTI)		U.L. 746A	170 Volts
U.L HV Track Rate		U.L. 746A	12.6 mm/Min.
Permittivity, 1MHz:	Condition A	D150	5.71
	D24/23		6.01
Dissipation Factor, 1MHz:	Condition A	D150	0.0479
	D24/23		0.0525
Permittivity, 1KHz:	Condition A	D150	6.93
	D24/23		8.28
Dissipation Factor, 1KHz:	Condition A	D150	0.1108
	D24/23		0.1912
U.L. Hot Wire Ignition		U.L. 746A	120+ seconds
U.L. High Amp Ignition		U.L. 746A	200 + Exposure
U.L. temperature Index:	Electrical		140° C
	Mechanical		140° C

Standard Sheet sizes are 36" x 48", 48" x 48", 48" x 72", & 48" x 96"

Ashtabula, Ohio 44004 440-997-6134 Fax 440-992-3614

All values are average test results from typical production material. No warranty is implied or guaranteed and testing is recommended for each application.

www.itenindustries.com

Imagineering With Plastics

March 29, 2019