

Iten Industries

Resiten® 113 Performance Values

<u>Properties</u>	<u>Test Condition</u>	<u>ASTM</u>	<u>Values</u>
Thickness			.125 inches
Tensile Strength:	Lengthwise	D638	24,900 psi
	Crosswise		16,700 psi
Flexural Strength:	Condition A Lengthwise	D790	29,300 psi
	Condition A Crosswise		23,200 psi
	D48/50 Lengthwise		24,300 psi
	D48/50 Crosswise		19,500 psi
Compressive Strength:	Lengthwise	D695	17,100 psi
	Crosswise		15,500 psi
Izod Impact (notched):	Condition A Lengthwise	D256	0.59 ft.lb./in.
	Condition A Crosswise		0.51 ft.lb./in.
	D48/50 Lengthwise		0.92 ft.lb./in.
	D48/50 Crosswise	D256	0.82 ft.lb./in.
	E48/50 Lengthwise		0.57 ft.lb./in.
	E48/50 Crosswise		0.48 ft.lb./in.
Water Absorption		D570	1.86% of weight
Specific Gravity		D792	1.40
U.L. Subject 94		UL94	94HB
Dielectric Strength		D149	170 Vpm
Dielectric Breakdown:	Condition A	D149	29.1 kV
	D48/50		4.0 kV
Arc Resistance:	Condition A	D495	32 seconds
	D48/50		9 seconds
U.L. Arc Resistance Rating:		D495	83 seconds
Comparative Track Index (CTI)		U.L. 746A	180 Volts
U.L. HV Track Rate		U.L. 746A	10.5 mm/Min.
Permittivity, 1MHz:	Condition A	D150	6.13
	D24/23		6.83
Dissipation Factor, 1MHz:	Condition A	D150	0.0549
	D24/23		0.4866
Permittivity, 1KHz:	Condition A	D150	9.02
	D24/23		13.60
Dissipation Factor, 1KHz:	Condition A	D150	0.2430
	D24/23		0.7470
U.L. Hot Wire Ignition		U.L. 746A	120+ seconds
U.L. High Amp Ignition		U.L. 746A	200+ Exposure
U.L. temperature Index:	Electrical		140° C
	Mechanical		140° C

Resiten® 113 meets or exceeds GE material specification A19B27C1 & C2

Standard Sheet sizes are 36" x 48", 48" x 48", 48" x 72", & 48" x 96"

Ashtabula, Ohio 44004 440-997-6134 Fax 440-992-3614
and

Addison, Illinois 60101 630-543-2880 Fax 630-543-1463

All values are average test results from typical production material. No warranty is implied or guaranteed and testing is recommended for each application.

itenindustries.com

Imageneering with Plastics

July 17, 2000