

Iten Industries

Resiten® 128TT Performance Values @ .093" Thick

<u>Properties</u>	<u>Test Condition</u>	<u>ASTM</u>	<u>Values</u>
Thickness			.093 inches
Flexural Strength:	Condition A Lengthwise	D790	27,300 psi
	Condition A Crosswise		21,500 psi
Compressive Strength:	Lengthwise	D695	16,900 psi
	Crosswise		15,200 psi
Izod Impact (notched):	Condition A Lengthwise	D256	0.49 ft.lb./in.
	Condition A Crosswise		0.46 ft.lb./in.
Water Absorption		D570	1.10% of weight
Specific Gravity		D792	1.38
U.L. Subject 94		UL94	94HB
Dielectric Strength		D149	450+ Vpm
Dielectric Breakdown:	Condition A	D149	95+ kV
	D48/50		10 kV
Arc Resistance:	Condition A	D495	129 seconds
Permittivity, 1MHz:	Condition A	D150	4.45
Dissipation Factor, 1MHz:	Condition A	D150	0.0390
U.L. temperature Index:	Electrical		130° C
	Mechanical		130° C

Standard Sheet sizes are 36" x 48", 48" x 48", 48" x 72", & 48" x 96"

Ashtabula, Ohio 44004 440-997-6134 Fax 440-992-3614

All values are average test results from typical production material. No warranty is implied or guaranteed and testing is recommended for each application.

www.itenindustries.com

Imagineering with Plastics

April 3, 2019